

**THEORETICAL COVERAGE
IN SQUARE METERS PER LITER**

Required Dry Film Thickness Per Coat (microns)

	25	50	75	100	125	150	175	200	225	250	275	300	325	350	275	400
100	40.0	20.0	13.3	10.0	8.0	6.7	5.7	5.0	4.4	4.0	3.6	3.3	3.1	2.6	2.7	2.5
95	38.0	19.0	12.6	9.5	7.6	6.4	5.4	4.8	4.2	3.8	3.4	3.1	3.0	2.8	2.6	2.4
90	36.0	18.0	12.0	9.0	7.2	6.1	5.1	4.5	4.0	3.6	3.2	3.0	2.8	2.6	2.4	2.3
85	34.0	17.0	11.3	8.5	6.8	5.7	4.9	4.3	3.7	3.4	3.1	2.8	2.6	2.5	2.3	2.1
80	32.0	16.0	10.5	8.0	6.4	5.4	4.6	4.0	3.5	3.2	2.9	2.6	2.5	2.3	2.2	2.0
75	30.0	15.0	10.0	7.5	6.0	5.0	4.3	3.8	3.3	3.0	2.7	2.5	2.3	2.2	2.0	1.9
70	28.0	14.0	9.3	7.0	5.6	4.7	4.0	3.5	3.1	2.8	2.5	2.3	2.2	2.0	1.9	1.8
65	26.0	13.0	8.7	6.5	5.2	4.4	3.7	3.3	2.9	2.6	2.3	2.2	2.0	1.9	1.8	1.6
60	24.0	12.0	8.0	6.0	4.8	4.1	3.4	3.0	2.6	2.4	2.2	2.0	1.9	1.7	1.6	1.5
55	22.0	11.0	7.3	5.5	4.4	3.7	3.1	2.8	2.4	2.2	2.0	1.8	1.7	1.6	1.5	1.4
50	20.0	10.0	6.7	5.0	4.0	3.4	2.9	2.5	2.2	2.0	1.8	1.7	1.6	1.5	1.4	1.3
45	18.0	9.0	6.0	4.5	3.6	3.0	2.6	2.3	2.0	1.8	1.6	1.5	1.4	1.3	1.2	1.1
40	16.0	8.0	5.3	4.0	3.2	2.7	2.3	2.0	1.8	1.6	1.4	1.3	1.2	1.16	1.08	1.0
35	14.0	7.0	4.7	3.5	2.8	2.3	2.0	1.8	1.5	1.4	1.3	1.2	1.1	1.00	0.95	0.88
30	12.0	6.0	4.0	3.0	2.4	2.0	1.7	1.5	1.3	1.2	1.1	1.0	0.9	0.87	0.81	0.75
25	10.0	5.0	3.3	2.5	2.0	1.7	1.4	1.3	1.1	1.0	0.9	0.83	0.78	0.73	0.68	0.63

**Theoretical Coverage Per Liter
(Square Meters)**